

LABORATORIES

Subsidiary of Mahaffey Associates Pty Ltd A.C.N. 001 629 036

TEST REPORT

Fax: (02) 9684 2310 Phone: (02) 0684 2422 Rydalmere NSW 2116 (PO Box 349) 4 Mary Pde

with its terms of registration. been performed in accordance by the National Association of This Laboratory is registered The tests reported here in have Testing Autorities, Australia



CLIENT: IDCM

SECTION: Sand / Cement Mix

Laboratory Trials

JOB No. 5966 DATE CAST: 07-08-2005

L10105

B>	REF No. CLIENT
26283 26284	BEMAC
08-08-2005 08-08-2005	DATE REC'D
05-11-2005 05-11-2005	DATE TESTED
90	AGE TESTED (Days)
89	DURATION OF STANDARD MOIST CURING (Days)
70 70	AVERAGE DIMENSION (mm)
59.5 64.0	COMPREHENSIVE STRENGTH (MPa)
2240 2240	MASS PER UNIT VOLUME - SSD (kg M ⁻³)

Samples Cast by Bemac.

not cylinders as required by part 9. Tested in accordance with AS 1012 Parts 9 and 12 (Method 1). Except that samples were cubes

Strength results calculated to the nearest 0.5 MPa.

SIGNED ...

11th November 2005 D. J. Wilmshurst