

Result are shown in the attached test reports.

The test results indicate the following.

1. Comprehensive Strength

The surface hardener has a compressive strength of 54.5 MPa at 7 days and 88.0 MPa at 28 days.

2. Slip Resistance


The surface hardener, when applied to the surface of concrete, provides a coefficient of friction, when tested wet, of 0.69. This substantially exceeds the minimum required by Australian Standard 3661.1, of 0.4.

3. Abrasion Resistance

The surface hardener, when applied to the surface of concrete, provides a mean abrasion index of 2.7. This is in the highest category for wear resistance, and indicates that the treated surface is suitable for high traffic areas such as major suburban pedestrian malls with a significant number of passes of high heel shoes.

We trust that this information is of assistance, however should you require anything further, please do not hesitate to contact the writer.

Yours faithfully,



D. R. Mahaffey