

# MAHAFFEY ASSOCIATES PTY LTD

*Incorporating Bemac Laboratories*

A.C.N 001 629 036

4 Mary Parade Rydalmere NSW 2116 PO Box 349 Rydalmere NSW 2116  
Telephone: (02) 9684 2422 Fax: (02) 9684 2310 Email: mahaffey@hlos.com.au

20th October 2005

IDCM PTY LTD

11 Meeks Rd

Marrickville NSW 2204

Attention: Mr C. Regas

Dear Sir,

Re: Testing of IDCM Colour Hardener

We have now concluded testing of a sample of IDCM colour hardener supplied by you.

The material was tested for the following.

- Compressive Strength
- Abrasion Resistance
- Slip Resistance

Sample of a sand: cement mix were prepared as a base for the colour hardener. Whilst this was setting, the colour hardener was applied to the surface and trowelled in, to simulate the manner in which it would be used on site. Samples were also made of the colour hardener for strength testing by mixing the material with water, and making it up to a stiff consistency. Cubes of this mix were then cast for strength testing.

The cubes were tested at 7 and 28 days, and the result are shown in the attached test reports. The samples with the colour hardener trowelled in were tested by Boral Resources for Abrasion Resistance and Slip resistance, and the results are shown in the attached and the